

Properties of MEK-P 50% (low activity)

ANALYTICAL

Aspect	Clear colorless liquid
Active Oxygen, %.....	9
PH	2.0-3.2
Density @ 20 ° C	1.10-1.12g/cm ³
Flash point @ ° C	90° C
Critical temperature	75°C

REACTIVITY

On 100 gm medium reactivity resin with 2 % MEK-P and 1% Cobalt octoate (1.5 %) in 25 ° C thermostatic bath the following result obtained

Gel time 18-21 min.
Peak temperature 138°C

N.B : since operating conditions in the use's plant are beyond our control , We cannot assume liabilities which may result from the use of our products

Rev. 07